

KIAAT TRAVERTINE FBS




PRODUCT RANGE CLASSIFICATION

CLAY FACE BRICK FBS - FACE BRICK STANDARD

Clay bricks that are selected or produced for their durability and uniformity of size and shape.



Following The South African National Standard (SANS 227:2007) for burnt clay face bricks.



BRICK TEXTURE - TRAVERTINE

A light textured finish with a natural clay grain appearance.



Variations in colour, texture, and size are natural characteristics of clay products and production variations can occur from batch to batch. Whilst every effort is made to provide brochures consistent with products delivered to site, they should be viewed as a guide only.

KIAAT TRAVERTINE FBS



SPECIFICATIONS

Size (length x width x height)	222 x 706 x	Classification	FBS
SANS	73mm 227:2007	ISO	9007:2075
Typical Compressive Strength	>22 MPa	Typical 24^{hr} Water Absorbtion	>7%
Moisture Expansion Category	II	Efflorescence Rating	Slight
Exposure Zone Suitability	7 - 3	Bricks per m² (excluding cutting & waste)	57
Factory Manufactured At	Middelwit,	Bricks per pallet	500
Average mass per brick	Mpumalanga 2.5kg	Available in Special Shaped Bricks	No



www.corobrik.co.za



Bateleur Estate, Nelspruit

Download the high-resolution swatches, BIM files and view more project photos | www.corobrik.co.za

Variations in colour, texture, and size are natural characteristics of clay products and production variations can occur from batch to batch. Whilst every effort is made to provide brochures consistent with products delivered to site, they should be viewed as a guide only.