

COROJEM CLASSIC BLEND FBS




**PRODUCT RANGE
CLASSIFICATION**

**CLAY FACE BRICK
FBS - FACE BRICK STANDARD**

Clay bricks that are selected or produced for their durability and uniformity of size and shape.



Following The South African National Standard (SANS 227:2007) for burnt clay face bricks.



**BRICK TEXTURE
TRAVERTINE**

A light textured finish with a natural clay grain appearance.



Variations in colour, texture, and size are natural characteristics of clay products and production variations can occur from batch to batch. Whilst every effort is made to provide brochures consistent with products delivered to site, they should be viewed as a guide only.

COROJEM CLASSIC BLEND FBS



SPECIFICATIONS

Size (width x length x height)	222 x 150 x 73mm	Classification	FBS
SANS	227:2007	ISO	9001:2015
Typical Compressive Strength	>23MPa	Typical 24^{hr} Water Absorbtion	>10%
Moisture Expansion Category	I	Efflorescence Rating	Slight-Moderate
Exposure Zone Suitability	1 - 2	Bricks per m² (excluding cutting & waste)	51
Factory Manufactured At	Rietvlei, Gauteng	Bricks per pallet	320
Average mass per brick	3.2kg	Available in Special Shaped Bricks	No



www.corobrik.co.za

[Download the high-resolution swatches, BIM files and view more project photos | www.corobrik.co.za](http://www.corobrik.co.za)

Variations in colour, texture, and size are natural characteristics of clay products and production variations can occur from batch to batch. Whilst every effort is made to provide brochures consistent with products delivered to site, they should be viewed as a guide only.