

# GOLDEN WHEAT TRAVERTINE FBX




## PRODUCT RANGE CLASSIFICATION

## CLAY FACE BRICK FBX - FACE BRICK EXTRA

Durable face bricks possessing a high degree of size, shape and colour uniformity.



Following The South African National Standard (SANS 227:2007) for burnt clay face bricks.



### BRICK TEXTURE TRAVERTINE

A light textured finish with a natural clay grain appearance.



Variations in colour, texture, and size are natural characteristics of clay products and production variations can occur from batch to batch. Whilst every effort is made to provide brochures consistent with products delivered to site, they should be viewed as a guide only.

# GOLDEN WHEAT TRAVERTINE FBX



## SPECIFICATIONS

<b>Size</b> (width x length x height)	222 x 106 x 73mm	<b>Classification</b>	FBX
<b>SANS</b>	227:2007	<b>ISO</b>	9001:2015
<b>Typical Compressive Strength</b>	>36MPa	<b>Typical 24<sup>hr</sup> Water Absorbtion</b>	>8%
<b>Moisture Expansion Category</b>	I	<b>Efflorescence Rating</b>	Nil
<b>Exposure Zone Suitability</b>	1 - 4	<b>Bricks per m<sup>2</sup></b> (excluding cutting & waste)	51
<b>Factory Manufactured At</b>	Kwastina, Gauteng	<b>Bricks per pallet</b>	464
<b>Average mass per brick</b>	2.2kg	<b>Available in Special Shaped Bricks</b>	Yes



View the range of Special Shaped Bricks | [www.corobrik.co.za](http://www.corobrik.co.za)



Groenkloof Retirement Village George

Download the high-resolution swatches, BIM files and view more project photos | [www.corobrik.co.za](http://www.corobrik.co.za)

Variations in colour, texture, and size are natural characteristics of clay products and production variations can occur from batch to batch. Whilst every effort is made to provide brochures consistent with products delivered to site, they should be viewed as a guide only.